

ITALIAN UPHOLSTERY COLLECTION

LEPLUS VIETNAM CO., LTD

In relation to normative of Leplus Vietnam Standard
Upholstery leather characteristics - Guide for the selection of leather for Furniture.

Articles Colours Size	Omega 10 4.5 - 5m ²	Torello 8 5.0 - 5.5m ²	New Valencia 2 5.0 - 5.5	Sector 10 5.0 - 5.5m ²	Type: Pigmented (Leather Top Grain)
-----------------------------	--------------------------------------	---	--------------------------------	---	--

			Normative	Result	Required
1	Determination of Thickness Omega Torello New Valencia Sector		ISO 2589		0.9-1.1 mm 1.1-1.3 mm 0.9-1.1 mm 0.9-1.1 mm
2	Tear Strength Horizontal Vertical		ISO 337-1		> = 20 N
3	Flexing Resistance Horizontal 50,000 cycles Vertical		ISO 5402		No Damage
4	Color Fastness to Light Apparatus SUNTEST XLS+ Xenon NXE 2201 Irradiance 250-765 W/m ² (300-800 nm), 2 Hours, 70°C, 510W/m ² Evaluation		ISO 105 B02		> = 4,5
5	Colour Fastness To Rubbing, Load 1000 Gram Dry 500 Cycles Pad Stain Leather Change Wet 80 Cycles Pad Stain Leather Change Perspiration 50 Cycles Pad Stain Leather Change Evaluation ISO 105A-03		ISO 11640 ISO 11641		> = 4 > = 4 > = 4 > = 4 > = 4 > = 4
6	Colour Fastness to spotting Watter Evaluation ISO 105 A03		ISO 15700		> = 3
7	Finish Adhesion Horizontal Vertical		ISO 11644		> = 2,5 N/Cm
8	Cold crack resistance of finish at -15°C		ISO 17233		No Cracks
9	Accelerated ageing 80°C 72 hours		ISO 17228		No Discoloration